

Technical manual №6.01. Version dated 10.2014.

Bitumen Primer TECHNOMICOL № 01

TU 5775-011-17925162-2003

Product description

Bitumen Primer TECHNOMICOL № 01 is a combination of oil bitumen and a specially selected organic solvents. It has a high penetration ability and short drying time.

Area of application

The primer is used for preparing (priming) of the substructures (concrete slab, cement-sand screed, etc.) before waterproofing with self-adhesive or other waterproofing materials.

Primer consumption —0.25 –0.35 l/m².



Main characteristics

Indicator name	Unit	Value	Testing method
Dry residue, in the range of	%	45-55	According to the GOST R 52487 (ISO 3251:2003)
Drying time, at most	h	12	GOST 19007-73
Relative viscosity, in the range of	s	15-40	According to the GOST 8420 on the viscosimeter V3-246 according to the GOST 9070, with the nozzle diameter 4 mm

Performance of works

According to the General Guidelines for design and construction of roofs with bitumen-polymer fusing materials TechnoNIKOL Corporation, the Guidelines for the waterproofing of underground structures TechnoNIKOL Corporation.

Temperature range from -20°C to +40°C. At temperature below +5°C withstand mastic in a warm room for at least 24 hours.

Drying time under standard conditions is not more than 12 hours.

Do not use near open flame. Work in well-ventilated areas. Avoid contact with skin and eyes.

Storage

Keep in a dry place, away from the sun light at temperature from -20°C to +30°C.

Guaranteed shelf life - 18 months.

Packaging Information

Metal eurobuckets 10 and 20 l.